

RECEIVED
CENTRAL FAX CENTER

APR 13 2007

AMENDMENTS TO THE CLAIMS

A Listing of Claims is provided as follows and will replace any previous listing.

No new matter has been added.

Listing of Claims:

1-100. (Canceled)

101. (Currently Amended) The eraser of claim ~~[[100]]~~ 128, wherein a filling rate of the ~~elastic material~~ eraser base material is set in the range of less than 100% with respect to the entire volume of the void portion in the porous structural material.

102. (Currently Amended) The eraser of claim ~~[[100]]~~ 128, wherein a filling rate of the ~~elastic material~~ eraser base material is set in the range from 60% to 80% with respect to the entire volume of the void portion in the porous structural material.

103. (Currently Amended) The eraser of claim ~~[[100]]~~ 128, wherein the skeleton portion of the skeleton structure has an average thickness of 10 μm to 50 μm , the void portion of the skeleton structure has an average pore size of 10 μm to 3 mm.

104-106. (Canceled)

107. (Currently Amended) The eraser of claim ~~[[100]]~~ 128, further comprising a surface hardness of 50 to 80 as measured according to JIS S6050, a sticking strength of 1.5 to 20 kgf, a coefficient of friction of not more than 0.8 and a wear rate of not less than 1%.

108-109. (Canceled)

110. (Currently Amended) The eraser of claim ~~[[100]]~~ 128, wherein the skeleton structure is continuous.

111. (Currently Amended) The eraser of claim ~~[[100]]~~ 128, wherein the ~~elastic material~~ eraser base material has a filling rate in a range from not less than 50% to less than 100% with respect to an entire volume of the void portion of the porous structural material.

112. (Currently Amended) The eraser of claim ~~[[100]]~~ 128, wherein the porous structural material contains a cross-sectional shape with virtually polygonal or virtually circular cells.

113. (Currently Amended) The eraser of claim ~~[[100]]~~ 128, wherein the porous structural material is a foamed structural material.

114. (Currently Amended) The eraser of claim ~~[[100]]~~ 128, wherein the porous structural material is a mesh structural material.

115. (Currently Amended) The eraser of claim ~~[[100]]~~ 128, wherein the porous structural material is a stereoscopic mesh structural material.

116. (Currently Amended) The eraser of claim ~~[[100]]~~ 128, wherein the porous structural material has a tensile strength of not more than 3 kgf/cm².

117. (Currently Amended) The eraser of claim ~~[[100]]~~ 128, wherein the porous structural material has an extension percentage of not more than 500%.

118. (Currently Amended) The eraser of claim ~~[[100]]~~ 128, wherein the porous structural material has a compression repulsive force of not less than 0.2 kgf.

119. (Currently Amended) The eraser of claim ~~[[100]]~~ 128, wherein the porous structural material has a tensile strength of not more than 3 kgf/cm², an extension percentage of not less than 500%, and a compression repulsive force of not less than 0.2 kgf.

120. (Currently Amended) The eraser of claim ~~[[100]]~~ 128, wherein at least one of the porous structural material and the ~~elastic material~~ eraser base material is colored.

121. (Currently Amended) The eraser of claim ~~[[100]]~~ 128, wherein the skeleton structure is constituted by a plurality of blocks of porous structural materials.

122. (Previously Presented) The eraser of claim 121, wherein the blocks have at least one shape selected from the group consisting of spherical, polygonal, and plate shapes.

123. (Currently Amended) The eraser of claim ~~[[100]]~~ 128, further comprising an exchanging-use eraser of a type selected from the group consisting of a feeding-type eraser, a knocking-type eraser, an eraser attached to an end of a mechanical pencil, and an electric-type eraser.

124. (Canceled)

125. (Currently Amended) The electric-eraser of claim ~~[[124]]~~ 131, wherein at least one of the porous structural material and the elastic material is colored.

126. (Currently Amended) The electric-eraser of claim ~~[[124]]~~ 131, wherein the skeleton structure is constituted by a plurality of blocks of porous structural materials.

127. (Currently Amended) The electric-eraser of claim ~~[[126]]~~ 131, wherein the skeleton structure is constituted by a plurality of blocks of porous structural materials, and the blocks have at least one shape selected from the group consisting of spherical, polygonal, and plate shapes.

128. (New) An eraser for erasing information, comprising:
a skeleton structure constituted by a skeleton portion and a void portion; and
an eraser-base material filled in the void portion,

wherein the skeletal portion of the skeleton structure is constituted by a porous structural material of organic polymer that comprises melamine-based resin,

the skeleton portion of the skeleton structure has an average thickness from 1 μm to 100 μm , and the void portion of the skeleton structure has an average pore size of 20 μm to 3 mm,

the eraser base material is selected from the group consisting of (a) a plastic-based eraser composition, (b) a rubber-based eraser composition, and (c) an elastomer-based eraser composition, and

(a) the plastic-based eraser composition comprises at least one of a vinylchloride resin and a vinylacetate resin, and comprises a filler,

(b) the rubber-based eraser composition comprises a rubber component, factice, sulfur, a vulcanizing accelerator, and a filler,

(c) the elastomer-based eraser composition comprises a thermoplastic elastomer and a filler.

129. (New) The eraser of claim 128, wherein the plastic-based eraser composition comprises a cured material of a sol-state composition by the vinylchloride resin and a plasticizer.

130. (New) The eraser of claim 128, wherein the filler is at least one chemical compound selected from the group of calcium carbonate, magnesium carbonate, silica, talc, clay, diatomaceous earth, quartz powder, alumina, alumina silicate, and mica.

131. (New) The eraser of claim 128, wherein the skeleton portion of said skeleton structure is constituted by the porous structural material of the organic polymer, where the organic polymer contains a thermosetting resin consisting of the melamine-based resin.

132. (New) An electric-eraser comprising:
an eraser holder; and

an eraser for erasing information, the eraser being attached to the holder, the eraser comprising:

a skeleton structure constituted by a skeleton portion and a void portion; and
an eraser-base material filled in the void portion,

wherein the skeletal portion of the skeleton structure is constituted by a porous structural material of organic polymer that comprises melamine-based resin,

the skeleton portion of the skeleton structure has an average thickness from 1 μm to 100 μm , and the void portion of the skeleton structure has an average pore size of 20 μm to 3 mm,

the eraser base material is selected from the group consisting of (a) a plastic-based eraser composition, (b) a rubber-based eraser composition, and (c) an elastomer-based eraser composition, and

(a) the plastic-based eraser composition comprises at least one of a vinylchloride resin and a vinylacetate resin, and comprises a filler,

(b) the rubber-base eraser composition comprises a rubber component, factice, sulfur, a vulcanizing accelerator, and a filler,

(c) the elastomer-based eraser composition comprises a thermoplastic elastomer and a filler.

133. (New) The electric-eraser of claim 132, wherein the filler is at least one chemical compound selected from the group of calcium carbonate, magnesium carbonate, silica, talc, clay, diatomaceous earth, quartz powder, alumina, alumina silicate, and mica.

134. (New) The electric-eraser of claim 132, wherein the skeleton portion of said skeleton structure is constituted by the porous structural material of the organic polymer, where the organic polymer contains a thermosetting resin consisting of the melamine-based resin.